

Industrial Pre-Woven



This uniquely styled slat is mechanically inserted into the chain link wire during the weaving process.

Once inserted, the wire is finished above and below the slat (either bow-knuckle or knuckle-over).

- Design**
Flat tubular plastic, pre-inserted into wire.
- Standard Heights**
4, 5, 6, 7, 8, 10 and 12 feet. Special heights available upon request.
- Installation**
Because this slat comes pre-inserted in the chain link fabric, just stretch the wire and tie it up. The result is a fully slatted fence with sight reduction.
- Wind Load and Privacy Factor**
Approximately 75%.
- Upon Special Request**
Available in bags that cover 25 linear feet for hand installation jobs.

Colors*



* Exact representation of slat colors in printing is difficult. Please refer to actual color samples for final matching.

**Chainlink Privacy Slats
Streetsboro, OH 44240
330.650.9226**

Industrial Pre-Woven Product Specifications



Slat Type	Slat Width	Mesh Size	Wire Gauge	Slats Per Crate	Approx. Coverage Per Box
Industrial	2 ³ / ₈ "	3 ¹ / ₂ " x 5"	9 or 10	2014 (106 pieces per bag)	475 linear feet

Materials

The Industrial Pre-Woven product is extruded from High Density Polyethylene (HDPE), color pigments and ultra violet (UV) inhibitors, specifically designed to retard the harmful effects of the sun and lengthen the life of the product.

Durability

Pexco PDS® HDPE Fence Products are resistant to: severe weather conditions, salt water, sand, road dirt, most acids, alcohol, alkaline, ammonia, petroleum distillates, and common environmental pollutants.

Maintenance

Pressure cleaning of surface contaminants is quickly accomplished with plain water.

Wind Load Disclaimer

Pexco will not be responsible for fence damage resulting from wind load conditions due to insufficient structural support.

Limited Warranty

Industrial slats carry a 25-year, pro-rata warranty against breakage under normal conditions. Write Pexco for full warranty information.

Note

Pexco is the manufacturer of the plastic slats only, we do not weave the wire. For pre-woven products, please contact your fence supplier or contact us for a supplier near you.

HDPE Technical Properties

Property	Value
Melt Index	(.6) A low melt index indicates improved stress and crack resistance.
Density	(.957) Polyethylene ranges anywhere from .914 to .960 in density. A higher density yields maximum stiffness without becoming overly brittle.
Minimum Temp.	(-76° F) Polyethylene stays flexible even at this temperature extreme.
Maximum Temp.	(250° F) Polyethylene does not distort until reaching this temperature.
Tensile Strength	(3,700 psi) Material will not suffer distortion at lesser loads or impacts.

**Chainlink Privacy Slats
Streetsboro, OH 44240
330.650.9226**

Contact your local fence professional for more information about our complete line of enhancement products.

